



X^e Whiteout Film Technical Data

● Solar Energy Transmission.....	10%
● Solar Energy Reflection - Exterior	49%
● Solar Energy Absorption	41%
● Visible Light Transmission	07%
● Visible Light Reflection - Exterior.....	58%
- Interior	58%
● UV Transmission	<1%
● Shading Coefficient (b Value)	0.25
● Emissivity	0.86
● U-Value (EN 673 W/m ² K)	5.59
● Glare Reduction.....	92%
● Coefficient of Total Energy Transmission (g Value)	0.21
● Thickness without Liner	81
● Total Solar Energy Rejected	78%

Characteristics & Benefits

- **White varnished tint:** Has a noble and elegant effect.
- **Opaque film:** Privacy protection
- **0% Visible Light Transmittance:** absolute darkness.
- **98% UV-protection:** Grants maximum colour stability of the film. Defers bleaching of items by reducing incidence of harmful UV radiation through the glass panel.
- **High-end, water soluble, extremely heat resistant adhesive with immediate agglomerating power when pressing:** Faster and easier removal of adhesive residues on the window pane after peeling off the film (time saving)
- Also suitable for safety & security.